

# CEPSASFALT 35/50 LF

## DEFINITION:

Cepsasfalt 35/50 LF bitumen is an asphalt binder that reduces specific gas emissions during production and paving work.

## SPECIFICATIONS:

Characteristics	Units	Standard	Min.	Max.
<b>Original binder</b>				
Penetration (25 °C; 100 g; 5s)	0,1 mm	EN 1426	35	50
Softening point	°C	EN 1427	50	58
Penetration index	-	EN 12591	-1,5	0,7
Fraass breaking point	°C	EN 12593	-	-5
Solubility	%	EN 12592	99,0	-
Flash point	°C	EN 2592	230	-
<b>RTFOT residue</b>				
Mass variation	%	EN 12607-1	-	0,5
Penetration (25 °C; 100 g; 5 s)	% p.o.	EN 1426	53	-
Variation in softening point	°C	EN 1427	-	11

## APPLICATIONS:

→ Hot bituminous mixes.

## RECOMMENDED WORKING TEMPERATURES:

- Mixing temperature (°C): 155-165.
- Working temperature (°C): 155-165.
- Compaction temperature (°C): 150- 160.
- Maximum heating temperature (°C): 170.