

# Emasfalt AR-2 (A65BR)

EMULSIONS ■ ANIONIC EMULSIONS

## DEFINITION:

Fast breaking anionic bituminous emulsion specially formulated for use in specific waterproofing solutions, compliant with the specifications contained in standard UNE 51603:2013 for type A65BR.

## SPECIFICATIONS:

Characteristics	Unit	Standard	Min.	Max.
<b>Original Emulsion</b>				
Particle polarity		UNE EN 1430	Negative	
Binder content per water content	%	UNE EN 1428	63	67
Efflux time (4 mm, 40°C)	s	UNE EN 12846	5	70
Residue on sieving (0.5 mm)	%	UNE EN 1429	-	0,10
Settling tendency (7 days storage)	%	UNE EN 12847	-	5
<b>Binder after distillation (UNE EN 1431)</b>				
Penetration (25 °C; 100 g; 5 s)	0,1mm.	UNE EN 1426	-	220
Softening point	°C	UNE EN 1427	35	-