

Emasfalt AL-1 (A60BFL)

EMULSIONS ■ OTHER COATS ■ PRIME COATS

DEFINITION:

Slow breaking cationic bituminous characteristics and degree of ageing of the material to be recycled as well as what percentage to use in the manufacturing of the recycled mix.

SPECIFICATIONS:

Characteristics	Unit	Standard	Min.	Max.
Original Emulsion				
Particle polarity	-	UNE EN 1430	Negative	
Binder content (per water content)	%	UNE EN 1428	58	62
Oil distillate content	%	UNE EN 1431	3	8
Efflux time (2 mm, 40 °C)	s	UNE EN 12846	15	70
Residue on sieving (0,5 mm)	%	UNE EN 1429	-	0.10
Settling tendency (7 days storage)	%	UNE EN 12847	-	10
Distillate waste (UNE EN-1431)				
Penetration (25 °C; 100 g; 5 s)	0.1mm	UNE EN 1426	-	220
Softening point	°C	UNE EN 1427	35	-