

Asphalt bitumen 15/25

Asphalt bitumen that complies with the specifications in the standard EN 13924 for 15/25 bitumen.

Applications:

- > High modulus mixtures

Recommended working temperatures:

- > Mixing temperature (°C): 165- 175
- > Working temperature (°C): 165- 175
- > Compaction temperature (°C): 160- 170
- > Maximum heating temperature (°C): 185

Specifications:

Characteristics	Units	Standard	Min.	Max.
Fresh binder				
Penetration (25 °C)	0,1 mm	EN 1426	15	25
Softening point (R&B)	°C	EN 1427	60	76
Penetration index	-	EN 12591	-1,5	+0,7
Solubility	%	EN 12592	99,0	-
Flash point	°C	EN ISO 2592	245	-
RTFOT residue				
Mass loss	%	EN 12607-1	-	0,5
Retained penetration	%	EN 1426	55	-
Variation in softening point	°C	EN 1427	-	10