

# Asphalt bitumen 160/220

Asphalt bitumen that complies with the specifications in the standard EN 12591 for 160/220 bitumen.

## Applications:

- > Chipping
- > Hot recycling
- > Fabrication of derivative bituminous products

## Recommended working temperatures:

- > Pumping temperature (°C): > 100
- > Storage and use temperature (°C): > 100
- > Maximum heating temperature (°C): 155

## Specifications:

Characteristics	Units	Standard	Min.	Max.
<b>Fresh binder</b>				
Penetration (25 °C)	0,1 mm	EN 1426	160	220
Softening point (R&B)	°C	EN 1427	35	43
Penetration index	-	EN 12591	-1,5	+0,7
Fraass point	°C	EN 12593	-	-15
Solubility	%	EN 12592	99,0	-
Flash point	°C	EN ISO 2592	220	-
<b>RTFOT residue</b>				
Mass loss	%	EN 12607-1	-	1,0
Retained penetration	% p.o.	EN 1426	37	-
Increase in softening point	°C	EN 1427	-	12



Revision No. 6 - Approved: 24/10/2025 - Next revision: 24/10/2030

For further information, please visit [www.moeve.es/en/](http://www.moeve.es/en/)

N.B: The recommendations in these technical specifications are purely for guidance and for general situations and Moeve takes no responsibility whatsoever for misuse. For individual cases, contact Moeve Technical Department.