

Elaster RAF AV (PMB 45/80 - 75)

High performance polymer modified bitumen complying with EN 14023 standard and obtained by chemical reaction between the base binder and an elastomeric polymer.

Applications:

- > Anti-cracking mixes
- > Rutting resistant Asphalt
- > SMA and AUTL mixtures
- > High Performance asphalt

Recommended working temperatures:

- > Mixing temperature (°C): 175- 185
- > Working temperature (°C): 175- 185
- > Compaction temperatura (°C): 170- 180
- > Maximum heating temperature (°C): 190

Specifications:

Characteristics	Units	Standard	Min.	Max.
Original binder				
Penetration (25 °C; 100 g; 5s)	0,1 mm	EN 1426	45	80
Softening point	°C	EN 1427	75	-
Fraass breaking point	°C	EN 12593	-	-15
Storage stability:		EN 13399		
• Difference in softening point	°C	EN 1427	-	5
• Difference in penetration (25 °C)	0,1 mm	EN 1426	-	13
Flash point	°C	EN ISO 2592	80	-
Elastic recovery (25 °C)	%	EN 13398	235	-
Force ductility (5°C)	J/cm ²	EN 13589	3	-
RTFOT residue				
Mass variation	%	EN 12607-1	-	1,0
Retained penetration	% p.o.	EN 1426	60	-
Increase in softening point	°C	EN 1427	-	10
Decrease in softening point	°C	EN 1427	-	5



Revision No. 5 - Approved: 24/10/2025 - Next revision: 24/10/2030

For further information, please visit www.moeve.es/en/
 N.B: The recommendations in these technical specifications are purely for guidance and for general situations and Moeve takes no responsibility whatsoever for misuse. For individual cases, contact Moeve Technical Department.