

INDUSFALT 70/40

DEFINITION:

Asphalt bitumen obtained by direct distillation or other refining methods and containing rheology modifiers specially designed to be used as base in industrial products.

SPECIFICATIONS:

| Characteristics | Units | Standard | Min. | Max. |
|------------------------------|--------|-------------|------|------|
| Softening point (R&B) | °C | EN 1427 | 65 | 75 |
| Penetration (25°C, 100g, 5s) | 0,1 mm | EN 1426 | 35 | 45 |
| Solubility in xylene | % | EN 12592 | 99 | - |
| Mass loss | % | EN 13303 | - | 0,5 |
| Flash point | °C | EN ISO 2592 | 250 | - |

APPLICATIONS:

- Raw material for waterproofing products in construction and membranes, joint sealing compounds and asphaltic paints.

RECOMMENDED WORKING TEMPERATURES:

- 110 - 160 °C.