

INDUSFALT 100/15

Asphaltic bitumen obtained by direct distillation or other refining methods specifically designed to be used as base in industrial products.

SPECIFICATIONS

Characteristics	Unit	Standard	MIN	MAX
Softening point (R&B)	°C	EN 1427	95	105
Penetration (25°C, 100g, 5s)	0,1 mm	EN 1426	10	20
Solubility in xylene	%	EN 12592	98	--
Mass loss	%	EN 13303	--	0,5
Flash point	°C	EN ISO 2592	250	--

RECOMMENDED WORKING TEMPERATURES

> 120 - 180°C.

APPLICATIONS

> Raw material for waterproofing products in construction and membranes, joint sealing compounds and asphaltic paints.