

Asphalt bitumen 60/70

Asphalt bitumen that complies with the specifications in the standard ASTM D-946 for B 60/70 bitumen.

Applications:

- › Hot bituminous mixtures

Recommended working temperatures:

- › Mixing temperature (°C):
150 - 160
- › Working temperature (°C):
150 - 160
- › Compaction temperature (°C):
145 - 155

Specifications:

Characteristics	Units	Standard	Min.	Max.
Fresh binder				
Penetration (25 °C)	0.1 mm	ASTM D5	60	70
Ductility	cm	ASTM D113	100	-
Solubility	%	ASTM D2042	99.0	-
Flash point	°F	EN ISO 2592	450	-
Resistance to hardening (163°C)		ASTM D1754		
Retained penetration	%	ASTM D5	47	-
Ductility	cm	ASTM D113	75	-